



Product Information

ESC-thane™ Compound U92K-BK Polyether based thermoplastic polyurethane

Property	Test Method	Units	Value
Hardness , Shore A	ASTM D2240		92A
Hardness , Shore D	ASTM D2240		45D
Specific Gravity	D792		1.19
Tensile Strength	D412	psi	5655
100% Modulus	D412	psi	1658
100% Modulus	D412	psi	2610
Elongation at Break	D412	%	580
Tear Resistance	D1938	pli	740
Split tear	D412	pli	
Compression Set 24 hours at 70°C (158°F)	ASTM D395B	%	26
Compression Set 24 hours at 100°C (212° F)	ASTM D395B	%	30
Flexural Modulus	ASTM D790	psi	
Rebound, Bashore	ASTM D2632	%	41
DIN Abrasion	DIN 4649	mm ³	20
Tg		F (C)	
Vicat Softening point	ASTM D1525	F (C)	
Operating Temperature			-40°F TO +250°F
Reinforcement			N0
Color			BLACK

The information provided in this data sheet corresponds to our knowledge on the subject at the date of this publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such materials used in combination with any other material, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specifications limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to do to determine the suitability of a specific compound for your particular purpose. Since Engineered Seals, LLC cannot anticipate all variation in actual end-use conditions ESC makes no warranties and assumes no liability in connection with any use of this information. Caution: Do not use this product in medical application involving permanent implantation in the human body.